



N O R D - C O M A T
Nord Construction Materials Laboratory

TE DHENA TEKNIKE TE LLACIT TE PARAPERGATITUR (Fuga) PER TU VENE NE ETIKETEN E THESIT.

Nr No	Pershkrimi Description	Vlerat Values
1	Granulometri <i>Granulometry</i>	0/2 mm
2	Klasa e fortesis <i>Strength class</i>	M35
3	Densiteti i llacit te fresket <i>The dry bulk density of fresh mortar</i>	$\pm 1.711 \text{ kg/m}^3$
4	Densiteti i thate i llacit te ngurtesuar <i>The dry bulk density of hardened mortar</i>	$\pm 1.570 \text{ kg/m}^3$
5	Konsistenca normale <i>Normal consistence</i>	$\geq 20 \%$
6	Rezistenca ne shtypje 28-ditore <i>Compressive strength 28-days</i>	$> 35 \text{ N/mm}^2$

NORD COMAT

HEAD OFFICE - Tirane; Mob: +355 69 5250337; NIPT: L 08501501 Q

Tirane, Dajt, Rruga "Muhamet Deliu" Pallat I Firmes "DODAJ", Kati I, afer Restorant Fresku; Tel:+355 44525511 E-mail:info@nordcomat.com